

# AquataPoxy A-10



## DESCRIPTION

AquataPoxy® A-10 is a solvent-free 100% solids, low viscosity epoxy primer or coating that may be applied to dry or damp surfaces.

## TYPICAL USES

Formulated for use as a primer on concrete, masonry or steel substrates in:

- Tunnels and pipelines
- Digesters
- Secondary containment
- Wastewater facilities
- Clarifiers
- Tanks
- Manholes
- Floors

## COLOR

The Part A Resin is clear; the Part B Curing Agent is amber. When mixed the product is a translucent honey color which dries to a transparent film.

## SOLIDS BY VOLUME

As supplied, solids by volume: 100% solids  
Volatile Organic Compounds: 0.0 pounds per gallon

## FILM THICKNESS

AquataPoxy A-10 is a 100% solids epoxy with zero shrinkage. Wet film thickness and dry film thickness are the same (i.e. 5 mils WFT = 5 mils DFT). A maximum of 8 mils per coat is recommended to prevent sagging. Recommended thickness when used as a primer or sealant is one or two coats at 2 - 5 mils each.

## COVERAGE

Theoretical coverage is 160 square feet per gallon at 10 mils wet film thickness. Actual surface coverage will depend on substrate porosity and roughness. Good painting practices suggest application of two coats for quality assurance. A wet film thickness gauge may be used to determine actual coating coverage.

## SURFACE PREPARATION

Prior to coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, neutralized surface suitable for the specified coating. The substrate must be free of all contaminants, such as oil, grease, rust, scale or deposits. Coating performance is proportional to the degree of surface preparation.

**STEEL** surfaces may require “Solvent Cleaning” (SSPC-SP 1) to remove oil, grease and other soluble contaminants. Chemical contaminants may be removed according to SSPC-SP 12/NACE No. 5. Identification of the contaminants along with their concentrations may be obtained from laboratory and field tests as described in SSPC-TU 4 “Field Methods for Retrieval and Analysis of Soluble Salts on Substrates”. Surfaces to be coated should then be prepared according to SSPC-SP 5/NACE No.1 “White Blast Cleaning” for

immersion service or SSPC-SP 10/NACE No. 2 “Near White Blast Cleaning” for all other service. In certain situations, an alternate procedure may be to use high (>5,000 psi) or ultrahigh (>10,000 psi) pressure water cleaning or water cleaning with sand injection and an approved rust inhibitor. The resulting anchor profile shall be 2.5-5.0 mils and be relative to the coating thickness specified.

**CONCRETE AND MASONRY** surfaces must be sound and contaminant-free with a surface profile equivalent to a CSP2 to CSP5 in accordance with ICRI Technical Guideline No. 03732. This can generally be achieved by abrasive blasting, shot blasting, high pressure water cleaning, water jetting or a combination of methods. Concrete exhibiting a moisture vapor emission rate greater than 3 lbs/1,000 ft<sup>2</sup>/24 hours (per ASTM F 1869) shall be primed with CM’s ConcretePlus CP815 waterborne primer before applying this product.

## MIX RATIO

Part A Resin:Part B Curing Agent mix ratio is 3:2 by volume.

## THINNING

**Do not thin with solvents.** If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained. Drum heaters may be used to heat larger quantities. Unmixed material should not be heated above 150°F.

## MIXING

Individually power mix both Part A and Part B containers, then measure out 3 parts of Part A to 2 parts of Part B by volume in a clean disposable pail. Use a heavy-duty drill with a Jiffy or Hanson plunge mixer and mix at 500-700 rpm for a minimum of one minute. Scrape the sides and bottom while transferring to a clean pail and continue mixing for at least another minute before application. Properly mixed material will be a uniform color.

## APPLICATION

Apply with epoxy-compatible brush, roller, plural component spray or other suitable method. For best results, apply to concrete when its temperature is stable or falling.

## POT LIFE

The pot life is 40 minutes for 1 gallon at 72°F. Longer working life is attained by mixing smaller batches and/or using cooler epoxy.

## CURE TIME

Thin film set time varies with substrate temperature and application thickness. Generally, the coating will be tack-free in 6 ½ hours at 72°F and dry-hard in about 9 hours.

# AquataPoxy A-10

## RECOAT TIME

This product may be recoated as soon as it becomes tacky but does not transfer to the finger. When applying multiple coats, do not allow more than 18 hours at 72°F substrate temperature to pass between coats, higher temperatures will shorten this window. Before recoating; inspect, clean and dry surface thoroughly to remove all contamination, including amine blush or condensation. If the recoat time is missed, clean and abrade surfaces prior to recoating.

## SUBSTRATE TEMPERATURE

Minimum recommended substrate temperature: 40°F  
Maximum recommended substrate temperature: 120°F

## TEMPERATURE RESISTANCE

Maximum recommended dry temperature: 200°F. Wet temperature resistance depends on chemical concentration and exposure time.

## CLEAN UP

Use acetone, MEK or xylene to clean tools. Wash immediately and thoroughly with soap and water to clean skin. Refer to the Material Safety Data Sheet for additional information on health and safety.

## AVAILABLE PACKAGES

Available in pints (5 pint kit), one gallon pails (5 gallon kit) and 5 gallon pails (25 gallon kit). Kits are supplied in the correct proportions of A & B; these two components must be mixed together before use.

## SHELF LIFE AND STORAGE

Product shelf life is 1 year from purchase date in original unopened containers, stored in a sheltered area between 60°F and 80°F (15°C and 27°C).

## SAFETY

Read the product's Material Safety Data Sheet (MSDS) for health and safety information before using. Strictly follow all notices on the MSDS and container label. If you do not fully understand the notices and procedures provided on the MSDS or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. The MSDS is available online at [www.cohesantmaterials.com](http://www.cohesantmaterials.com).

## TYPICAL PROPERTIES<sup>(1)</sup>

DESCRIPTION	METHOD	RESULT
Mandrel Bend Test, 4-9 mils	ASTM D 522	Passed ½" mandrel
Tensile Elongation	ASTM D 522	8%
Compressive Strength	ASTM D 695	6,900 psi
Hardness, Shore D	ASTM D 2240	77
Taber Abrasion, CS-17 wheel	ASTM D 4060, 1 kg load/1,000 cycles	<80 mg loss
Adhesion, Concrete	ASTM D 4541	Substrate Failure

(1) Typical properties are to be considered as representative of current production and should not be construed as specifications.

Warranty and Disclaimer: Cohesant Materials Inc. ("Cohesant Materials") warrants its products to be free of manufacturing defects in accord with applicable Cohesant Materials quality control procedures and that they meet the formulation standards of Cohesant Materials. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. If, within one year from purchase, any product is proven defective, Cohesant Materials, at its sole option, will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to Cohesant Materials written directions.

**THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL COHESANT MATERIALS INC. BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST COHESANT MATERIALS INC. MAY BE COMMENCED MORE THAN ONE YEAR AFTER THE CLAIM ARISES.**