

# ConcretePlus™ CP835 Re-surfacer

High performance epoxy coatings and repair systems for concrete and more.

## DESCRIPTION

ConcretePlus™ CP835 Re-surfacer is a zero-VOC, professional grade, two component, medium-high viscosity epoxy with good chemical resistance. Its long pot life allows ample time to repair minor surface irregularities in concrete or steel and cinder-block surfacing.

## TYPICAL USES

- Patching concrete pits, small holes or pockmarks
- Stationary cracks and joints
- Feathering lapped steel plate joints
- Filling voids and cinder-block surfacing
- Repaired surfaces may be immediately topcoated

## COLOR

The Part A Resin is white; the Part B Curing Agent is black. When mixed the product is gray.

## SOLIDS BY VOLUME

As supplied, solids by volume: 100% solids  
Volatile Organic Compounds: 0.0 pounds per gallon

## APPLICATION THICKNESS

CP835 is a 100% solids epoxy with zero shrinkage. Wet film thickness and dry film thickness are the same (i.e. 40 mils WFT = 40 mils DFT). Depending on substrate type and profile, a maximum of 120 mils per coat is recommended to prevent sagging. Typical recommended thickness will vary from 40-120 mils based on surface roughness.

## COVERAGE

Coverage is 40 square feet per gallon when applied at 40 mils as flooring. Actual surface coverage will depend on substrate porosity and roughness. A wet film thickness gauge may be used to determine application thickness.

## MIX RATIO

Part A Resin:Part B Curing Agent mix ratio is 1:1 by volume.

## MIXING

Power mix each component separately, then measure out 1 part of Part A to 1 part of Part B by volume in a clean pail. Use a heavy-duty drill with a Jiffy or Hanson plunge mixer and mix at 500-700 rpm for a minimum of one minute. Scrape the sides and bottom while transferring to a clean pail and continue mixing for at least another minute before application. Properly mixed material will be a uniform color.

## THINNING

**Do not thin with solvents.** If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained. Unmixed material should not be heated above 150°F.



## AVAILABLE PACKAGES

Available in one gallon pails (2 gallon kit) and five gallon pails (10 gallon kit). Kits are supplied with the proper amounts of A & B; these two components must be mixed together before use.

## SURFACE PREPARATION

The best coating performance is achieved with good surface preparation. Before coating, the substrate must be prepared in a manner that provides a uniform, clean, contaminant free, sound, neutralized surface suitable for the specified coating.

Metal surfaces may require solvent cleaning to remove oil, grease and other soluble contaminants. Surfaces should be prepared to “white metal” for immersion service or “near white metal” for all other service. The resulting anchor profile should be 2-5 mils.

Concrete must be sound and free of dust, dirt, oil, grease, marine growth or deposits with a surface profile similar to 60-grit sandpaper. This can generally be achieved by abrasive blasting, shot blasting, high pressure water cleaning, water jetting or a combination of methods. Concrete floors exhibiting a moisture vapor emission rate greater than 3 lbs/1,000 ft<sup>2</sup>/24 hours (per ASTM F 1869) should be primed with CP815 waterborne primer before applying CP835.

## APPLICATION

Apply with a trowel, putty knife, brush, epoxy-compatible roller, airless or air-assisted spray or other suitable method. For best results, apply when the concrete temperature is stable or falling.

## POT LIFE

The pot life is 45 minutes for ½ gallon at 72°F. Longer

# ConcretePlus™ CP835 Re-surfacer

working life is attained by mixing smaller batches and/or using cooler epoxy.

## CURE TIME

Generally, the coating will be tack-free in 4 ½ hours on a 72°F substrate and dry-hard in 8 hours. Thin film set time varies with substrate temperature and application thickness.

## RECOAT TIME

This product may be recoated with itself as soon as it becomes tacky to the touch but does not transfer to the finger. When applying multiple coats, do not allow more than 18 hours at 72°F substrate temperature to pass between coats, higher temperatures will shorten this window. Clean the surface to remove any contamination before recoating. If the recoat time is missed, abrade and clean the surface prior to coating.

## SUBSTRATE TEMPERATURE

Minimum recommended substrate temperature: 40°F  
Maximum recommended substrate temperature: 120°F

## TEMPERATURE RESISTANCE

Maximum recommended dry temperature: 160°F. Wet temperature resistance depends on chemical concentration and exposure time.

## CLEAN UP

Use acetone, MEK or xylene to clean tools. Wash immediately and thoroughly with soap and water to clean skin. Refer to the Material Safety Data Sheet for additional information on health and safety.

## SHELF LIFE AND STORAGE

Product shelf life is 1 year from purchase date in original unopened containers, stored in a sheltered area between 60°F and 80°F (15°C and 27°C).

## SAFETY

Read the product's Material Safety Data Sheet (MSDS) for health and safety information before using. Strictly follow all notices on the MSDS and container label. If you do not fully understand the notices and procedures provided on the MSDS or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. The MSDS is available online at [www.cohesantmaterials.com](http://www.cohesantmaterials.com).

## TYPICAL PROPERTIES<sup>(1)</sup>

DESCRIPTION	METHOD	RESULT
Tensile Strength	ASTM D 638	5,600 psi
Tensile Ultimate Elongation	ASTM D 638	4.4%
Compressive Strength	ASTM D 695	9,900 psi
Flexural Strength	ASTM D 790	8,300 psi
Hardness, Shore D	ASTM D 2240	86
Adhesion, Concrete	ASTM D 4541	Substrate Failure
Adhesion, Steel (SSPC-SP 5)	ASTM D 4541	3,000 psi

(1) Typical properties are to be considered as representative of current production and should not be construed as specifications.

Warranty and Disclaimer: Cohesant Materials Inc. ("Cohesant Materials") warrants its products to be free of manufacturing defects in accord with applicable Cohesant Materials quality control procedures and that they meet the formulation standards of Cohesant Materials. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. If, within one year from purchase, any product is proven defective, Cohesant Materials, at its sole option, will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to Cohesant Materials written directions.

**THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL COHESANT MATERIALS INC. BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST COHESANT MATERIALS INC. MAY BE COMMENCED MORE THAN ONE YEAR AFTER THE CLAIM ARISES.**